



Analysis report Physical

Pag 1/1

Analysis report: C6230812

Date report : 2-7-2021

Date sampled : 27-5-2021

Date of receipt : 27-5-2021

Sample code : RFS210527825

Sampled by : not by GAC

Analysis : Limited physical method potting

Description : **Mineral wool substrate Ekover Ground**

Sample type:

Copy to :

Order nr :

Location: PJSC Uralasbest

Uralskaya Street 66

Asbest City of Sverdlovsk Region

Analysis results

Moisture content (% w/w) : 0.3

Organic matter (% DM) : 0.2

Bulk density (kg/m³) : 73

Shrinkage (%) : -

Pore fraction (%) : 97

pF 1,0 (-10 cm)

Waterfraction %	Airfraction %	Water ratio g water / g OM
61	36	197

Supplied characteristics

Product :

Category :

Section :

Status :